



### TEST REPORT

DATE: 06/05/2009

TEST NUMBER: 121628

CLIENT	Schutz NA.
--------	------------

TEST METHOD CONDUCTED	ASTM D2 047-99 Jame Machine - Coeficient of Friction on Flooring Material
-----------------------	---

DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Luxury Vinyl Plank with Schutz Slipnomor Finish
COLOR	-----
ROLL	-----
CONSTRUCTION	-----
FIBER	-----
BACKING	-----
REFERENCE	


#### GENERAL PRINCIPLE

This test was used to measure the relative static coefficient of friction by using the James Machine.

#### TEST RESULTS

TEST ENVIRONMENT	69° F 50% Relative Humidity
------------------	-----------------------------

Sensor Materials	Dry
Leather 0.	7

APPROVED BY: 

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.